

Product datasheet

Property*	Basis Weight	SCT CD	Burst	Moisture	Cobb 60
Method	ISO 536	ISO 9895	ISO 2758	DIN EN 20287	ISO 535
Unit	g/m ²	kN/m	kPa	%	g/m ²
Variation	+/- 3%	-10%	-10%	+/- 1pt	+/- 10pt
	170	2,94	416	8	40

*Values subject to production variation

Available from Q3 2024

Norske Skog Bruck production

- PM3 – 5300 mm
- Capacity: 210.000 tons containerboard
- Basis weights: 90 – 175 g/m²
- Reel width: 800 – 2850 mm
- Reel diameter: 1450 mm

www.norskeskog.com

September 2024

