

Product datasheet

Property*	Basis Weight	SCT CD	CMT	Burst	S Test	Cobb	Moisture
Method	ISO 536	ISO 9895	ISO 7236	ISO 2758	DIN 5014	ISO 535	DIN EN 20287
Unit	g/m ²	kN/m	N	kPa	kN/m	g/m ²	%
Variation	+/- 3%	-10%	-10%	-10%	-10%	+/- 10 pt	+/- 1 pt
	90	1,57	135	212	0,76	35	8
	95	1,64	150	226	0,84	35	8
	100	1,73	165	239	0,91	35	8
	105	1,82	179	251	0,99	35	8
	110	1,91	187	264	1,06	35	8
	115	1,98	196	277	1,14	35	8
	120	2,08	204	290	1,22	35	8
	125	2,16	212	303	1,29	35	8
	130	2,23	220	316	1,37	35	8
	135	2,31	228	327	1,45	35	8

*Values subject to production variation

Available from H1 2025

Norske Skog Golbey production

- PM1 – 8700 mm
- Capacity: 550.000 tons containerboard
- Basis weights: 80 – 135 g/m²
- Reel width: 500 – 3350 mm
- Reel diameter: 1400 mm

www.norskeskog.com

December 2024



launch into
a new sphere